



SDS)

SJ6200

2024-01-26

2024-02-25

4.8

GB/T 16483-2008 GB/T 17519-2013

1.

POLYESTER RESIN

SJ6200

CAS

8

241008

0553-5316333

0553-5316330

SDS

ASJ_SDS@126.com

[http //www.shen-jian.com](http://www.shen-jian.com)

0553-5316333

2.

GB 13690-2009 GB 30000-2013

GHS

GHS

■

P261
P271
P272
P280

■

P302+P352
P333+P317
P342+P316
P362+P364

■

P410+P403

■

P501

vPvB

3. /

/

1

		%	GHS
	CAS: 552-30-7 EC: 209-008-0		H317- H318-

1,2,4	REACH #: 01-2119489422-34 Index 607-097-00-4 RTECS #: DC2050000	1.0	H334- H335-
-------	---	-----	----------------

8

4.

15

/

“ ”(11)

5.

CO₂

/

(MSHA/NIOSH)

6.

8

“ ”

8

13

7

(8)

30°C (86°F)

8.

1,2,4-

CAS. 552-30-7

8h

[%(v/v)]
(kPa)
(=1)
(=1) 1.2
(g/cm³) 1.2 (23°C)
600 750 kg/m3
(mg/L)
(mg/L)
(°C) 350
(°C) 350

(°C) 350

VOC

10.

(7)

()

11.

/
/

1,2,4			

CAS 552-30-7

12.

/ (Koc)
PBT vPvB
PBT
vPvB

13.

	—	—	—

MARPOL 73/78 II IBC

15.

[illegible]

A	2015	2015	92						
B	2022		2022	8					
C			2019	60					
D	(1 2)		2011	95		2013	12		
E		445	2016		666				
F									
G					2020	1			
H			2017	83		2020	47		
I	2017		2017	05 11					
J	(2019)		2019	07 05					
K	(2023)					2022	12 29 28		

[illegible]

AIIIC

DSL

DRAFT

EINECS

ENCS

IECSC

KECL

NCI

INSQ

NZloc

PICCS

TCSI

TSCA

TSCA

	A	B	C	D	E

A

B

A B C E

C

D

“ ” PIC

E

UNECE

16.

2 9 15

2024 02 25

2021 06 28

4.8

1 (ICSC), <http://www.ilo.org/dyn/icsc/showcard.home>2 <http://www.iarc.fr/>3 OECD <http://www.echemportal.org/echemportal/index?page>4 CAMEO <http://cameochemicals.noaa.gov/search/simple>5 : <http://chem.sis.nlm.nih.gov/chemidplus/chemidlite.jsp>6 <http://cfpub.epa.gov/iris/>7 <http://www.phmsa.dot.gov/hazmat/library/erg>8 GESTIS- <http://gestis-en.itrust.de/>

CAS–

TSCA– TSCA

PC-STEL–

PC-TWA–

DNEL–

IARC–

RPE–

PNEC–

LC₅₀– 50%LD₅₀–50%

NOEC–

EC₅₀–50%

PBT–

POW– /

BCF– (BCF)

vPvB–

CMR–

IMDG–

